

Repository Istituzionale dei Prodotti della Ricerca del Politecnico di Bari

Sustainable bio-hydrothermal sequencing treatment for asbestos-cement wastes

This is a post print of the following article

Original Citation:

Sustainable bio-hydrothermal sequencing treatment for asbestos-cement wastes / Spasiano, Danilo; Luongo, Vincenzo; Race, Marco; Petrella, Andrea; Fiore, Saverio; Apollonio, Ciro; Pirozzi, Francesco; Fratino, Umberto; Piccinni, Alberto F. - In: JOURNAL OF HAZARDOUS MATERIALS. - ISSN 0304-3894. - STAMPA. - 364:(2019), pp. 256-263. [10.1016/j.jhazmat.2018.10.025]

Availability: This version is available at http://hdl.handle.net/11589/149445 since: 2021-03-01

Published version DOI:10.1016/j.jhazmat.2018.10.025

Publisher:

Terms of use:

(Article begins on next page)

14 July 2024

1	Simultaneous treatment of agro-food and asbestos-cement waste by the
2	combination of dark fermentation and hydrothermal processes
3	Marco Race ^a , Danilo Spasiano ^{b*} , Vincenzo Luongo ^a , Andrea Petrella ^b , Saverio Fiore ^c ,
4	Francesco Pirozzi ^a , Umberto Fratino ^b , Alberto F. Piccinni ^b
5	
6	^a Dipartimento di Ingegneria Civile, Edile ed Ambientale, Università di Napoli Federico
7	II, Via Claudio, 21, 80125, Napoli, Italy.
8	^b Dipartimento di Ingegneria Civile, Ambientale, Edile, del Territorio e di Chimica,
9	Politecnico di Bari, Via E. Orabona, 4, 70125, Bari, Italy.
10	^c Institute of Methodologies for Environmental Analysis, National Research Council of
11	Italy, Tito Scalo, Potenza, Italy.
12	* Corresponding Author: tel.: (+39) 0805963240; <u>danilo.spasiano@poliba.it</u> .
13	
14	Abstract
15	The inadequate management of asbestos-cement products (ACP) and/or wastes (ACW)
16	generates hazardous airborne dusts. For this reason, the EU is promoting the removal of
17	ACP from utilities, public and private buildings and is looking for innovative ACW
18	treatments alternative to the landfilling. The simultaneous treatment of ACW and orange
19	pulp or cheese whey was attempted with a mesophilic dark fermentation (DF) process
20	followed by a 12 h hydrothermal (HT) treatment carried out with the addition of lactic or
21	oxalic acid at 100 °C and ambient pressure. The DF of orange pulp or cheese whey in the
22	presence of 5 g L $^{\text{-1}}$ ACW lasted 171 h and led to the production of 4 L_{H_2} and 5 L_{H_2} per
23	litre of solution, respectively. During the DF, the dissolution of the ACW matrix was
24	almost completed, and the partial collapse of the asbestos fibres was observed. Both the

organic acids that were added during the HT tests at a concentration ≥ 2.5 g L⁻¹ completely destroyed the asbestos fibres. However, when 1.25 g L⁻¹ lactic or oxalic acid was added before the HT tests, few fibre fragments were found, and their chemical composition differed from that of chrysotile.

29

30 Keywords: orange pulp; cheese whey; oxalic acid; chrysotile; hydrogen; asbestos-

31 cement waste treatment.

32

33 **1. Introduction**

Chrysotile, also called white asbestos, is the most used type of asbestos, and it is 34 considered to be a human carcinogen (Donaldson et al., 2013; Stayner et al., 2013). 35 Chrysotile consists of sheets of Mg(OH)₂ (brucite-like sheets) bonded to sheets of SiO₂, 36 and it is characterized by a layered structure that is wrapped around itself to form a tubular 37 fibre structure with a spiral section (Falini et al., 2004). In a very recent paper, the 38 39 adoption of the DF process as a pretreatment of an acid-infused HT phase was proposed to destroy the chrysotile fibres contained in ACW to save energy and reagents (Spasiano 40 et al., 2017). Indeed, the biological DF treatment led to the conversion of glucose in CO₂-41 42 and H₂-rich biogas and organic acids (OA) (Saleem et al., 2018), which dissolved all of the calcium-based compounds from the cement matrix and part of the brucite-like sheets 43 of the chrysotile fibres constituting the Eternit sample (Spasiano, 2018). Consequently, 44 during the acid-infused HT treatment that was carried out at 100 °C under ambient 45 pressure, the amount of sulfuric acid, which was required to completely dissolve the 46 suspended brucitic layers was halved with respect to a previous finding (Nam et al., 2014). 47 Similar results were obtained when 1.25 g L⁻¹ malic or lactic acid was added instead of 48

the same amount of sulfuric acid, but in these cases, the anaerobic digestion (AD) of the 49 HT effluents led to an additional source of energy in the form of bio-methane (Spasiano 50 et al., 2019). Notably, besides to chemicals savings, this treatment train led to the 51 production of both bio-hydrogen and bio-methane, which can energetically support the 52 53 HT treatment. Consequently, the adoption of a DF stage followed by the HT and AD treatments could overcome the high energy and/or reagents requirement issues of the 54 conventional ACW treatments (Spasiano and Pirozzi, 2017) and support the application 55 56 of the recently introduced ACW treatment train at the industrial scale.

57 The above mentioned studies were carried out by adding glucose as a biodegradable substrate in a $[C_6H_{12}O_6]/[ACW]$ mass ratio equal to 12 during the DF. Even if an aqueous 58 59 solution of glucose could simulate the molasses produced by sugar refineries (Sen et al., 2019), the production is not enough to meet the needs of this treatment train, since the 60 quantity of ACW to be disposed is very high. For example, the ACW to be treated in Italy 61 and in Flanders, which is a Belgian region, equals 3.0×10^7 ton and 3.7×10^6 ton, 62 respectively (OVAM, n.d.; Plescia et al., 2003). However, instead of glucose, other 63 64 biodegradable substrates could be used during the DF, such as the organic fraction of 65 municipal solid waste (Shin et al., 2004; Gomez et al., 2006), wastewater sludge (Cai et al., 2004; Wang et al., 2019), agricultural lignocellulosic biomasses (Kumar et al., 2015; 66 67 Motte et al., 2015; Hu et al., 2018), and agro-food wastes (Buitrón et al., 2014; Mamimin 68 et al., 2016; Ghimire et al., 2017).

The aim of this study was to demonstrate the potential biotechnological valorisation of two biodegradable wastes, cheese whey and orange pulp, which were used as substrates for the DF process to produce H_2 and the required OAs necessary for an efficient ACW treatment. Cheese whey represents approximately 80–90% of the milk used during the

production of cheese and casein and, to date, represents a waste (Colombo et al., 2016). 73 In particular, the global cheese whey production in 2016 was almost equal to 200×10^6 ton 74 75 y⁻¹ and the FAO evaluated a constant 3% increase of cheese whey production in the last 21 years (Domingos et al., 2018). Even if 50% of this by-product is converted into useful 76 77 products, such as human and animal feed, the rest is disposed of as a waste (Nikodinovic-Runic et al., 2013). Citrus pulp is a waste that is derived from juice-making industries and 78 79 represents approximately 50% of the processed fruit weight (Mantzouridou and Paraskevopoulou, 2013). The global citrus pulp production may reach 25×10⁶ ton y⁻¹ 80 (Taghizadeh-Alisaraei et al., 2017), and only a small part of the pulp that is derived from 81 the squeezing of citrus fruits is pelletized and sold for animal feeding (Mamma et al., 82 83 2008). Consequently, as in the case of cheese whey, the proposed treatment train could valorise and treat this by-product, which is generally landfilled with a cost that is 84 approximatively equal to 10 USD ton⁻¹ (Rossi et al., 2009). 85

The DF effluents from the biological conversion of orange pulp or cheese whey have been 86 processed with an acid-infused HT treatment to completely dissolve the brucite-like 87 88 layers of chrysotile fibres and their suspended fragments. In agreement with the findings 89 of a previous work in which sulfuric, malic and lactic acid were tested (Spasiano et al., 2019), in this study, lactic acid was adopted since it seems to be a good compromise in 90 91 terms of costs, bioavailability, efficiency at dissolving brucitic layers, and bio-methane 92 production during the final AD treatment. However, in this work, oxalic acid was also tested because it costs 50-80% less than lactic acid and it could be considered to be a 93 94 green chemical. Indeed, oxalic acid could be produced from waste biomasses (André et al., 2010; Musiał et al., 2011) or from the reduction of carbon dioxide (Angamuthu et al., 95 2010). Additionally, the oxalic acid biodegradation in anaerobic conditions could 96

generate a methane rich biogas (Dinsdale et al., 2000). Notably, the adoption of oxalic
acid instead of lactic or malic acid would both lower the costs of reagents and contribute
to the production of methane during the AD of the HT effluents.

The novelty of this work consists in the evaluation of the real feasibility of the proposed 100 101 process adopting real biodegradable wastes instead of a synthetic glucose solution, which was already tested in our previous papers (Spasiano, 2018; Spasiano et al., 2019). This 102 103 aspect is crucial because, if the process have to be scaled using glucose as sacrificial 104 biodegradable substrate, the process may not be convenient, or at least less convenient 105 than using agro-food industry wastes. Furthermore, for the first time the evolution of the chrysotile structure degradation has been evaluated at the end of the main steps of the 106 107 treatment train by means of SEM and EDX analysis.

108

109 2. Materials and methods

110 **2.1. Materials**

Oxalic acid (≥99%) and lactic acid (85%), which were manufactured by Sigma-Aldrich.
The sulfuric acid (98%) in the preparation of the high-pressure liquid chromatography
(HPLC) eluent were used. In all of the reported experiments and in the dilution for
analytical procedures, demineralized water was adopted as the solvent.

The inoculum that was adopted for the DF experiments was attained by a thermal pretreatment of the digestate, which was derived from an anaerobic digester that was used to treat the wastewater and the biodegradable wastes produced by the dairy farm 'Davide Colangelo', located in southern Italy. In particular, the pretreatment was carried out at 105 °C and lasted 1.0 h (Ghimire et al., 2015). The digestate characterization highlighted the total solids (TS) and volatile solids (VS) at concentrations of 50.3 g L⁻¹ and 26.5 g 121 L^{-1} , respectively, with the initial pH value of 7.8, and finally, the initial dissolved calcium and magnesium concentrations were 276 mg L⁻¹ and 626 mg L⁻¹, respectively. 122 123 The characterization of the ACW sample that was used in this study, which was reported elsewhere (Spasiano, 2018), showed the presence of chrysotile fibres and Mg²⁺ and Ca²⁺ 124 concentrations that were equal to 3.1 $\%_{w/w}$ and 30.0 $\%_{w/w}$, respectively. 125 The orange pulp and cheese whey that were adopted in this experimental campaign are 126 characterized by a COD equal to 173.5 g kg⁻¹ and 77.5 g L⁻¹, respectively. Additionally, 127 128 the characterizations of the two substrates, which are reported in Table 1S, agreed with 129 previous findings (Wong et al., 1978; de Moraes Barros et al., 2012). Once received, the substrates were stored at -18 °C, and an orange peel was blended before use to easily 130 131 manage the specific bio-reactor's feeding procedure.

132

133 2.2. Analytical methods

The dissolved magnesium and calcium ion concentrations were measured by flame 134 (acetylene/air) atomic absorption spectrometry (FAAS). Bio-H₂ concentration in the 135 136 produced biogas was evaluated by Varian Star 3400 gas chromatography (GC). The concentrations of OAs were evaluated by using a HPLC technique. The adopted 137 equipment consisted of an absorbance detector, a gradient pump and a chromatography 138 139 oven where a cation-exchange column was housed. The solids collected after the DF and 140 HT processes were analysed with a FESEM-EDX electronic microscope after a golden 141 sputtering was carried out with a Sputter Quorum Q150 under Ar atmosphere. The TS, 142 VS, and COD values were measured according to APHA standard methods (Association, 1998). A pH-meter (HI 98190 pH/ORP; Hanna Instruments) was used to monitor the pH 143 of the solutions. 144

145 Detailed information is presented in the Supporting Materials.

146

147 2.3. Experimental apparatus

Dark fermentation bioreactors consisted of a 2.0 L borosilicate glass bottle closed with 148 149 airtight screw caps having two sampling tubes to allow for the withdrawal of liquid and gaseous samples. To guarantee a food to microorganism ratio (F/M), expressed as the 150 COD substrate (g)/VS inoculum (g), close to 2.6 (Spasiano et al., 2017), 500 mL of 151 152 inoculum was mixed with 407 mL of cheese whey or 182 g of orange pulp. The solutions 153 were made up to the volume of 1.0 L with distilled water and were purged with pure N_2 for 30 min to ensure anaerobic conditions. Successively, the bio-reactors were 154 155 continuously stirred at 370 rpm and maintained at 35 ± 1 °C. The DF experiments were carried out under batch-wise conditions until the cumulative H₂ production reached a 156 157 plateau to re-activate the inoculum. Later, the stirring of the solution was interrupted for 158 2 h to allow the sedimentation of most of the biomass, and the reactors were fed in fedbatch conditions. In particular, 500 mL of supernatant was removed and replaced by 500 159 160 mL of a water solution containing 182 g of orange pulp or 407 mL of cheese whey. This 161 procedure was repeated when the cumulative H₂ production reached a plateau for the 162 second time, and 5.0 g of ACW was added to each bioreactor together with the 163 biodegradable substrate.

The DF pretreatments of ACW lasted until the cumulative H_2 production reached the plateau for the third time, and the resulting solutions representing the effluent of the DF processes were used for HT experimentation. To this purpose, 100 mL of the afforded solution was heated in a round bottom flask equipped with a glass condenser cooled with tap water (≈ 15 °C). In particular, the flasks were immersed into an oil bath with a thermostat at 100 °C and were magnetically stirred. Once the solutions reached the required temperature, oxalic acid or lactic acid was added to the solutions with a concentration in the range of 0–5.0 g L^{-1} . Once withdrawn with a syringe, the samples were centrifuged, filtered, diluted, and, finally, analysed.

173

174 **3. Results and discussion**

175 **3.1. DF treatment**

176 Due to the orange pulp and cheese whey bio-degradation, the H₂ production at the end of 177 the inoculum activation phase (45 h) was 2.6 L and 2.4 L, respectively (Figure 1). This 178 result is in accordance with other studies on DF of real waste biomasses (Kumar et al., 2017; Ghimire et al., 2016) where low H_2 yields and high OA accumulation can be 179 achieved with respect to the case of synthetic glucose-based solutions fermentation. DF 180 of soluble biodegradable compounds, such as sugars, usually lead to the production of 181 acetic acid, butyric acid, propionic acid and ethanol as main by-products (Kumar et al., 182 183 2017). The known biological routes for H_2 production usually depend on the bacterial 184 inoculum and substrate characteristics (Ghimire et al., 2016, Ghimire et al., 2017). Due to the complexity of the real-scale derived inoculum and the organic substrates used in 185 this work, the stoichiometry of the process is far to be well known. Based on glucose 186 fermentation by fermentative bacteria (Eq. 1-3 from Costello et al. (1991)), it is possible 187 to assess that the presence of acetic (Eq. 1) and butyric (Eq. 2) acids in the culture medium 188 189 is more favourable for H₂ production optimization.

190
$$C_6H_{12}O_6 \rightarrow CH_3CH_2CH_2COOH + 2CO_2 + 2H_2,$$
 (Eq. 1)

191 $C_6H_{12}O_6 + 2H_2O \rightarrow 2CH_3COOH + 2CO_2 + 4H_2,$ (Eq. 2)

192 $C_6H_{12}O_6 \rightarrow 2CH_3CHOHCOOH.$

8

(Eq. 3)

When other fermentation pathways are performed, as in the case of mixed culture-real 193 194 substrate fermentation, low H₂ yields are achieved and other by-products, such as lactic 195 acid (Eq.3), can be accumulated in the bioreactors. In addition, using high F/M ratios it is possible to favour acids accumulation within the culture medium with uncomplete 196 197 substrate conversion. This was the aim of DF phase in this work, where high OA concentrations were accumulated for the successive dissolution phase of the ACW 198 199 treatment. After feeding the bioreactors in semi-batch conditions, the H₂ production decreased. Indeed, with the second and third loads of cheese whey, the H₂ volumes 200 generated in the bioreactor were 2.1 L and 0.5 L, respectively, while lower H₂ volumes 201 were produced by using orange pulp as a biodegradable substrate. This behaviour could 202 203 be ascribed to the production of other OAs, such as lactic, which led to a decrease in the pH (Figure 2) and the consequent slowdown of bio-H₂ production. Moreover, the lower 204 H₂ production during the DF of orange pulp could be due to the presence of orange peel 205 oil, which was mainly constituted by D-limonene, a monoterpene that is toxic to 206 fermenting microorganisms (Zema et al., 2018). In particular, among the other OAs 207 208 typically produced during the DF process (Figure 2), the presence of 1468 mg L⁻¹ caproic 209 acid at the end of the DF of the orange peel confirms this hypothesis. D-Limonene, by interacting with the membrane structure of specific microorganisms such as Escherichia 210 211 coli and Salmonella enterica, led to the change in the membrane lipid profile and to an 212 increase in the caproic acid content to more than 50% (Di Pasqua et al., 2007).

The inhibitory effect of D-limonene also affected the amount and the speciation of produced OAs during the DF. This aspect is highly relevant because inorganic trace elements can add additional inhibitory effects on microbial consortia operating in anaerobic conditions (Maharaj et al., 2018). Indeed, when cheese whey was used as the

substrate, the final amount of OAs was higher than when using orange pulp as feedstock. 217 Specifically, the molar ratio among butyric acid and acetic acid (B/A) in the effluents of 218 the last cycle was 1.21, which is a value that is close to the optimal B/A ratio (1.5) that 219 was previously evaluated (Hawkes et al., 2007). On the other hand, during the DF of 220 221 orange peel, the OA production decreased by almost 40%, and the B/A ratio at the end of the biological phase was also equal to 0.66. These results are higly relevant as they can 222 be used as experimental base for the understanding of the biochemical behaviour of mixed 223 224 culture consortia and the definition of mathematical models (Frunzo et al., 2019; Mattei 225 et al., 2018; Kostrytsia et al., 2018).

However, in both cases, the OAs produced during the DF phase attached the calcium and 226 227 magnesium compounds contained in the ACW sample that was added 100 h after the beginning of the experiments. Indeed, as shown in Figure 3, most of the Ca-based 228 compounds that constituted the cement matrix of the ACW sample were dissolved, since 229 90% of the theoretical Ca amount in the suspended ACW was found dissolved as Ca^{2+} in 230 both of the effluents of the biological phase. This results is in agreement with the 231 232 biogeochemical mechanisms of deterioration of concrete due to the metabolic activity of 233 some microorganisms, which leads to the production of OAs that facilitate the calcium complexation and dissolution (Sand, 1997; Jia et al., 2019). Specifically, this 234 235 phenomenon can contribute to the biodeterioration of cement pipe in drinking water distribution systems (Wang et al., 2011), of buildings and monuments (Dyer, 2017). 236

At the same time, 41.5% and 36.4% of the magnesium constituting the brucitic layer of white asbestos contained in the ACW was found to be dissolved in the DF effluents from cheese whey and orange peel, respectively. Also in this case, the dissolution of the brucitic layer could be ascribed to the metal extracting action of the OAs produced during the DF. Indeed, a similar biodeterioration mechanism was observed in the environment on asbestos and asbestiform minerals exposed to the action of some organisms (bacteria, fungi and lichens), whose metabolites with acidic and chelating functions (such as, oxalic acid, pulvinic and norstictic acid) attack and extract metals from the asbestos structure (Favero-Longo et al., 2013; Mohanty et al., 2018).

In particular, as shown in Figure 3, the net concentration of calcium and magnesium ions $([Ca^{2+}]_n \text{ and } [Mg^{2+}]_n)$ at the end of the DF was normalized with respect to the theoretical calcium and magnesium concentration suspended in the solid state after the addition of 5 g L⁻¹ ACW ($[Mg^{2+}]_t$ and $[Ca^{2+}]_t$) as follows:

250
$$\frac{[Mg^{2+}]_{n}}{[Mg^{2+}]_{t}} = \frac{[Mg^{2+}]_{171h} - [Mg^{2+}]_{100h}}{155 \text{ mg L}^{-1}}$$
(Eq. 4)

251
$$\frac{[Ca^{2+}]_{n}}{[Ca^{2+}]_{t}} = \frac{[Ca^{2+}]_{171h} - [Ca^{2+}]_{100h}}{1500 \text{ mg L}^{-1}}$$
(Eq. 5)

where $[Mg^{2+}]_{171h}$ and $[Ca^{2+}]_{171h}$ represent the concentrations of dissolved cations at 252 the end of the biological pretreatments, while $[Mg^{2+}]_{100h}$ and $[Ca^{2+}]_{100h}$ are the 253 concentration of the ions dissolved in the solutions just before the 5 g L⁻¹ ACW addition. 254 Even when a partial dissolution of the brucitic layers was observed in both cases, 255 256 asbestos-like fibres were still present. Indeed, SEM analysis carried out on the suspended solids contained in the DF effluents showed some fibres that were characterized by a 257 258 morphology that is very similar to that of chrysotile (Figure 1S). In agreement with the lower amount of dissolved magnesium, the fibres found in the effluents of the DF that 259 260 were carried out in the presence of orange peel (Figures 1Sc-d) seemed larger than in the other case. Additionally, the EDX analysis carried out on the fibres (sites S1-S6 of Figure 261 1S) revealed an Mg/Si weight ratio that was close to the theoretical Mg/Si ratio of pure 262

chrysotile (1.298 g_{Mg}/g_{Si}). Indeed, the Mg/Si ratios were all in the range of 1.185-1.017 263 g_{Mg}/g_{Si} , except in the case of a thin fibre (site S4) that had a Mg/Si ratio of 0.814 g_{Mg}/g_{Si} . 264 Most likely, the attack of the OAs produced during the DF begins with the defibration of 265 266 the chrysotile and the consequent generation of increasingly thinner bundles of fibrils. 267 Due to the larger specific surface area, the latter may be attacked faster by the OAs, with a consequent decrease in the Mg/Si ratio. Although the Mg/Si ratios were lower than the 268 269 theoretical value and the chrysotile fibres seemed to have suffered an alteration, an HT 270 treatment should be carried out.

271

272 **3.2.** Acid-infused hydrothermal treatment

273 To ensure the collapse of all the residual chrysotile fibres in the effluents of the biological pretreatment, HT treatment tests were carried out at 100 °C under ambient pressure. In 274 275 particular, the effects of lactic and oxalic acid additions during the HT treatment of the DF effluents were investigated. As reported in Figure 4, a slight effect of the acid type 276 277 was observed during the tests. Indeed, higher magnesium concentrations were detected at the beginning of the experiments, when oxalic acid was used instead of lactic acid. Since 278 279 the two organic acids used in this study are characterized by the same molecular weight, 280 using the same loading condition for each specific HT test caused the molar 281 concentrations to coincide. Consequently, the different efficiencies of the adopted acids 282 could be ascribed to the acidity and the chelating properties of the two compounds. Oxalic 283 acid has pK_a values equal to 1.25 and 4.14 (Faria et al., 2008), while the pK_a value of lactic acid is 3.86 (Luongo et al., 2019; Gonzalez et al., 2008). Additionally, oxalic acid 284 285 has more pronounced chelating properties than lactic acid due to the presence of two carboxylic groups. 286

Apart from the different hydrogen productions, the biodegradable substrates that were 287 added during the DF pretreatment also play a key role in the HT step. Indeed, when cheese 288 whey was used, the HT treatments of the DF effluents (Figure 4a) result in a more efficient 289 brucitic sheet dissolution with respect to the treatment of the DF effluents carried out by 290 291 using orange peel as the biodegradable substrate (Figure 4b). Indeed, with the addition of 1.25 g L⁻¹ lactic acid or oxalic acid to the effluents of the DF carried out with cheese 292 293 whey, almost 91% of brucitic sheets dissolution was achieved after 12 h of HT treatment 294 at 100 °C. On the other hand, when orange peel was used as the substrate, with the 295 addition of the same loads of lactic and oxalic acid, almost 87% of brucite-like sheets were dissolved. These results are probably due to the high amount of OAs produced 296 297 during the DF process: the more OAs are produced during the DF treatment, the higher is the dissolution efficiency of the brucitic sheets at the end of both the DF and HT 298 299 treatments (Table 1).

Regardless of the biodegradable substrate that was used during the DF, no chrysotile-like 300 fibres were found during the SEM analysis of the solids that were withdrawn at the end 301 of the HT processes carried out with the addition of 5.0 g L⁻¹ and 2.5 g L⁻¹ lactic acid. On 302 303 the other hand, SEM analysis of the suspended solids collected after the HT process was carried out with the addition of only 1.25 g L⁻¹ lactic acid showed the presence of few 304 305 small fibres, which were similar to chrysotile. These fibrils, which are shown in Figure 306 2S, were smaller and thinner than those found in the DF effluents that are shown in Figure 1S. Moreover, the Mg/Si weight ratios of the fibrils indicates strong damage to the 307 308 brucitic layer. Indeed, the EDX analysis carried out on these fibre fragments (sites S7-S10 of Figure 2S) highlighted the Mg/Si ratios in the range of 0.86 $g_{Mg/g_{Si}}$ (site S9) to 309 0.52 g_{Mg}/g_{Si} (site S7). 310

Even if most of the chrysotile fibres collapsed and their fragments have a chemical composition that is different from that of white asbestos, the addition of 1.25 g L⁻¹ lactic acid or, supposedly, oxalic acid, may not guarantee the complete destruction of all of the asbestos fibres. Moreover, there is no information about the toxicity of the fragments that are shown in Figure 2S. Consequently, it would be advisable to extend the duration of the treatment or to increase the concentrations of acids to avoid any environmental issues that are related to the treatment train.

318

319 4. Conclusion

320 The DF of orange pulp and cheese whey resulted in an effective pretreatment for the acid-infused 321 HT phase of ACWs. Indeed, the biological treatment of these two agro-food wastes led to the production of OAs and H₂, which can reduce the reagent and energy costs of the HT treatment. 322 323 In comparison with the DF of orange pulp, which is rich in D-limonene, higher H₂ and organic acid production rates were observed when the cheese whey was used as the substrate. In both 324 cases, the addition of 2.5 g L⁻¹ lactic or oxalic acid, before an HT treatment lasting 12 h, allowed 325 for the effective treatment of 5 g L^{-1} ACW. On the other hand, when lactic and oxalic acid were 326 added at the concentration of 1.25 g L⁻¹, a few fibre fragments were found in HT effluents, and 327 their chemical composition differed from that of chrysotile. 328

329

330 Acknowledgement

331 The Authors thank Prof. Paolo Calabrò and Prof. Luigi Frunzo for providing the332 biodegradable substrates and for technical support.

333

335 **References**

André, A., Diamantopoulou, P., Philippoussis, A., Sarris, D., Komaitis, M.,
Papanikolaou, S., 2010. Biotechnological conversions of bio-diesel
derived waste glycerol into added-value compounds by higher fungi:
production of biomass, single cell oil and oxalic acid. Ind. Crops Prod.
31, 407–416.

- Angamuthu, R., Byers, P., Lutz, M., Spek, A.L., Bouwman, E., 2010.
 Electrocatalytic CO₂ conversion to oxalate by a copper complex.
 Science (80-.). 327, 313–315.
- Association, A.P.H., 1998. APHA. 1998. Stand. methods Exam. water wastewater 20.
- Buitrón, G., Prato-Garcia, D., Zhang, A., 2014. Biohydrogen production
 from tequila vinasses using a fixed bed reactor. Water Sci. Technol. 70,
 1919–1925.
- Cai, M., Liu, J., Wei, Y., 2004. Enhanced biohydrogen production from
 sewage sludge with alkaline pretreatment. Environ. Sci. Technol. 38,
 3195–3202.
- Colombo, B., Sciarria, T.P., Reis, M., Scaglia, B., Adani, F., 2016.
 Polyhydroxyalkanoates (PHAs) production from fermented cheese
 whey by using a mixed microbial culture. Bioresour. Technol. 218, 692–
 699.

356	Costello, D.J., Greenfield, P.F. and Lee, P.L., 1991. Dynamic modelling of
357	a single-stage high-rate anaerobic reactor-I. Model derivation. Water
358	research 25(7), 847–858.
359	De Moraes Barros, H.R., de Castro Ferreira, T.A.P., Genovese, M.I., 2012.
360	Antioxidant capacity and mineral content of pulp and peel from
361	commercial cultivars of citrus from Brazil. Food Chem. 134, 1892-
362	1898.
363	Di Pasqua, R., Betts, G., Hoskins, N., Edwards, M., Ercolini, D., Mauriello,
364	G., 2007. Membrane toxicity of antimicrobial compounds from essential
365	oils. J. Agric. Food Chem. 55, 4863–4870.
366	Dinsdale, R.M., Hawkes, F.R., Hawkes, D.L., 2000. Anaerobic digestion of
367	short chain organic acids in an expanded granular sludge bed reactor.
368	Water Res. 34, 2433–2438.
369	Domingos, J.M., Puccio, S., Martinez, G.A., Amaral, N., Reis, M.A.M.,
370	Bandini, S., Fava, F., Bertin, L., 2018. Cheese whey integrated
371	valorisation: Production, concentration and exploitation of carboxylic
372	acids for the production of polyhydroxyalkanoates by a fed-batch
373	culture. Chemical Engineering Journal, 336, 47–53.
374	Donaldson, K., Poland, C.A., Murphy, F.A., MacFarlane, M., Chernova, T.,
375	Schinwald, A., 2013. Pulmonary toxicity of carbon nanotubes and

- asbestos—similarities and differences. Adv. Drug Deliv. Rev. 65, 2078–
 2086.
- 378 Dyer, T., 2017. Deterioration of stone and concrete exposed to bird excreta-
- Examination of the role of glyoxylic acid. International Biodeterioration
 & Biodegradation 125, 125–141.
- ³⁸¹ Falini, G., Foresti, E., Gazzano, M., Gualtieri, A.F., Leoni, M., Lesci, I.G.,
- Roveri, N., 2004. Tubular-Shaped Stoichiometric Chrysotile
 Nanocrystals. Chem. Eur. J. 10, 3043–3049.
- Faria, P.C.C., Órfão, J.J.M., Pereira, M.F.R., 2008. Activated carbon
 catalytic ozonation of oxamic and oxalic acids. Appl. Catal. B Environ.
 79, 237–243.
- Favero-Longo, S.E., Turci, F., Fubini, B., Castelli, D., Piervittori, R., 2013.
- Lichen deterioration of asbestos and asbestiform minerals of serpentinite rocks in Western Alps. International Biodeterioration & Biodegradation 84, 342–350.
- Frunzo, L., Fermoso, F.G., Luongo, V., Mattei, M.R., Esposito, G., 2019.
- ADM1-based mechanistic model for the role of trace elements in anaerobic digestion processes. J. Environ. Manage. 241, 587–602.
- 394 Ghimire, A., Frunzo, L., Pontoni, L., d'Antonio, G., Lens, P.N.L., Esposito,
- G., Pirozzi, F., 2015. Dark fermentation of complex waste biomass for

biohydrogen production by pretreated thermophilic anaerobic digestate.

- 397 J. Environ. Manage. 152, 43–48.
- 398 Ghimire, A., Sposito, F., Frunzo, L., Trably, E., Escudié, R., Pirozzi, F.,
- Lens, P.N., Esposito, G., 2016. Effects of operational parameters on dark
 fermentative hydrogen production from biodegradable complex waste
 biomass. Waste Manag. 50, 55–64.
- 402 Ghimire, A., Luongo, V., Frunzo, L., Pirozzi, F., Lens, P.N.L., Esposito, G.,
- 2017. Continuous biohydrogen production by thermophilic dark
 fermentation of cheese whey: Use of buffalo manure as buffering agent.
 Int. J. Hydrogen Energy 42, 4861–4869.
- Gomez, X., Moran, A., Cuetos, M.J., Sanchez, M.E., 2006. The production
 of hydrogen by dark fermentation of municipal solid wastes and
 slaughterhouse waste: a two-phase process. J. Power Sources 157, 727–
 732.
- Gonzalez, M.I., Alvarez, S., Riera, F.A., Alvarez, R., 2008. Lactic acid
 recovery from whey ultrafiltrate fermentation broths and artificial
 solutions by nanofiltration. Desalination 228, 84–96.
- Hawkes, F.R., Hussy, I., Kyazze, G., Dinsdale, R., Hawkes, D.L., 2007.
- 414 Continuous dark fermentative hydrogen production by mesophilic
 415 microflora: principles and progress. Int. J. Hydrogen Energy 32, 172–
 416 184.

417	Hu, BB., Li, MY., Wang, YT., Zhu, MJ., 2018. High-yield
418	biohydrogen production from non-detoxified sugarcane bagasse:
419	Fermentation strategy and mechanism. Chem. Eng. J. 335, 979–987.
420	Jia, R., Unsal, T., Xu, D., Lekbach, Y., Gu, T., 2019. Microbiologically
421	influenced corrosion and current mitigation strategies: A state of the art
422	review. International Biodeterioration & Biodegradation 137, 42-58.
423	Kostrytsia, A., Papirio, S., Frunzo, L., Mattei, M.R., Porca, E., Collins, G.,
424	Lens, P.N., Esposito, G., 2018. Elemental sulfur-based autotrophic
425	denitrification and denitritation: microbially catalyzed sulfur hydrolysis
426	and nitrogen conversions. J. Environ. Manage. 211, 313-322.
427	Kumar, G., Bakonyi, P., Periyasamy, S., Kim, S.H., Nemestóthy, N., Bélafi-
428	Bakó, K., 2015. Lignocellulose biohydrogen: practical challenges and
429	recent progress. Renew. Sustain. Energy Rev. 44, 728-737.
430	Kumar, G., Sivagurunathan, P., Pugazhendhi, A., Thi, N.B.D., Zhen, G.,
431	Chandrasekhar, K., Kadier, A., 2017. A comprehensive overview on
432	light independent fermentative hydrogen production from wastewater
433	feedstock and possible integrative options. Energy conversion and
434	management 141, 390-402.
435	Luongo, V., Palma, A., Rene, E.R., Fontana, A., Pirozzi, F., Esposito, G. and
436	Lens, P.N., 2019. Lactic acid recovery from a model of Thermotoga
437	neapolitana fermentation broth using ion exchange resins in batch and

- 438 fixed-bed reactors. Separation Science and Technology 54(6), 1008–
 439 1025.
- 440 Maharaj, B.C., Mattei, M.R., Frunzo, L., van Hullebusch, E.D. and Esposito,
- G., 2018. ADM1 based mathematical model of trace element
 precipitation/dissolution in anaerobic digestion processes. Bioresour.
 Technol. 267, 666–676.
- Mamimin, C., Jehlee, A., Saelor, S., Prasertsan, P., Sompong, O., 2016. 444 Thermophilic hydrogen production from co-fermentation of palm oil 445 mill by and decanter cake effluent Thermoanaerobacterium 446 thermosaccharolyticum PSU-2. Int. J. Hydrogen Energy 41, 21692-447 21701. 448
- Mamma, D., Kourtoglou, E., Christakopoulos, P., 2008. Fungal
 multienzyme production on industrial by-products of the citrusprocessing industry. Bioresour. Technol. 99, 2373–2383.
- Mantzouridou, F., Paraskevopoulou, A., 2013. Volatile bio-ester production
 from orange pulp-containing medium using Saccharomyces cerevisiae.
 Food Bioprocess Technol. 6, 3326–3334.
- 455 Mattei, M.R., Frunzo, L., D'acunto, B., Pechaud, Y., Pirozzi, F., Esposito,
- G., 2018. Continuum and discrete approach in modeling biofilm
 development and structure: a review. Journal of Mathematical Biology
 76(4), 945–1003.

 Christofidou-Solomidou, M., Willenbring, J.K., 2018. Siderophore- mediated iron removal from chrysotile: Implications for asbestos toxicity reduction and bioremediation. J. Hazard. Mater. 341, 290–296. Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 		Monanty, S.K., Gonneau, C., Salamatipour, A., Pietrofesa, R.A., Casper, B.,
 mediated iron removal from chrysotile: Implications for asbestos toxicity reduction and bioremediation. J. Hazard. Mater. 341, 290–296. Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	460	Christofidou-Solomidou, M., Willenbring, J.K., 2018. Siderophore-
 toxicity reduction and bioremediation. J. Hazard. Mater. 341, 290–296. Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	461	mediated iron removal from chrysotile: Implications for asbestos
 Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	462	toxicity reduction and bioremediation. J. Hazard. Mater. 341, 290–296.
 dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	463	Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of
 deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	464	dry dark fermentation and mechanical pretreatment for lignocellulosic
 acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	465	deconstruction: an innovative strategy for biofuels and volatile fatty
 Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	466	acids recovery. Appl. Energy 147, 67-73.
 bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	467	Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin
 469 cultivated on biodiesel-derived waste composed of glycerol and fatty 470 acids. Appl. Clay Sci. 52, 277–284. 471 Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	468	bleaching in an oxalic acid enriched medium by Aspergillus niger
 acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	469	cultivated on biodiesel-derived waste composed of glycerol and fatty
471 Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of	470	acids. Appl. Clay Sci. 52, 277–284.
	471	Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of
470 asherton containing reafing slate and the feasibility of using reavaled	472	asbestos-containing roofing slate and the feasibility of using recycled
472 aspestos-containing rooming state and the reastority of using recycled		waste sulfuria agid I Hazard Mater 265 151 157
 472 assestos-containing rooming state and the reasonity of using recycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 	473	waste suffuire acid. J. Hazard. Mater. 203, 131–137.
 472 asbestos-containing rooming state and the reastority of using recycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 474 Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., 	473 474	Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A.,
 472 asbestos-containing footing state and the feasibility of using feetycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 474 Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., 475 Connor, K.E.O., 2013. Carbon-rich wastes as feedstocks for 	473 474 475	Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A.,Connor, K.E.O., 2013. Carbon-rich wastes as feedstocks for
 472 asbestos-containing footing state and the feasibility of using feetycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 474 Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., 475 Connor, K.E.O., 2013. Carbon-rich wastes as feedstocks for 476 biodegradable polymer (polyhydroxyalkanoate) production using 	473 474 475 476	 Waste sulfulle acid. J. Hazard. Matel. 203, 131–137. Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., Connor, K.E.O., 2013. Carbon-rich wastes as feedstocks for biodegradable polymer (polyhydroxyalkanoate) production using
 472 asbestos-containing fooring state and the feasibility of using feetycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 474 Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., 475 Connor, K.E.O., 2013. Carbon-rich wastes as feedstocks for 476 biodegradable polymer (polyhydroxyalkanoate) production using 477 bacteria, in: Advances in Applied Microbiology. Elsevier, pp. 139–200. 	473 474 475 476 477	 Waste sulfulle acid. J. Hazard. Matel. 203, 131–137. Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., Connor, K.E.O., 2013. Carbon-rich wastes as feedstocks for biodegradable polymer (polyhydroxyalkanoate) production using bacteria, in: Advances in Applied Microbiology. Elsevier, pp. 139–200.
 472 asbestos-containing fooring state and the feasibility of using feetycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 474 Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., 475 Connor, K.E.O., 2013. Carbon-rich wastes as feedstocks for 476 biodegradable polymer (polyhydroxyalkanoate) production using 477 bacteria, in: Advances in Applied Microbiology. Elsevier, pp. 139–200. 478 OVAM, n.d. State of the art: asbestos - Possible treatment methods in 	473 474 475 476 477 478	 Waste sulfulite acid. J. Hazaid. Matel. 203, 131–137. Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., Connor, K.E.O., 2013. Carbon-rich wastes as feedstocks for biodegradable polymer (polyhydroxyalkanoate) production using bacteria, in: Advances in Applied Microbiology. Elsevier, pp. 139–200. OVAM, n.d. State of the art: asbestos - Possible treatment methods in
470 asherton containing reafing slate and the feasibility of using reaval	472	asbestos-containing roofing slate and the feasibility of using recycl
470 asherton containing reafing data and the feasibility of using reavalad	472	asbestos-containing roofing slate and the feasibility of using recycled
472 aspestos-containing rooming state and the reastority of using recycled		waste sulfurie agid I Hazard Mater 265, 151, 157
 472 assestos-containing rooming state and the reasonity of using recycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 	473	Waste sumune actu. J. mazatu. Mater. 205, 151–157.
 472 assestos-containing rooming state and the reastority of using recycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 	473	waste suffuire acid. J. Hazard. Mater. 203, 131–137.
 472 asbestos-containing rooming state and the reastority of using recycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 474 Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., 	473 474	Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A.,
 472 asbestos-containing rooming state and the reastority of using recycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 474 Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., 	473 474	Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A.,
 472 assestos-containing rooming state and the reasibility of using recycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 474 Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., 	473 474	Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A.,
 472 asbestos-containing rooming state and the reastority of using recycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 474 Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A., 	473 474	Nikodinovic-Runic, J., Guzik, M., Kenny, S.T., Babu, R., Werker, A.,
 472 assestos-containing rooming state and the reastority of using recycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 474 Nikodinovic-Runic I Guzik M Kenny ST Babu R Werker A 	473 474	Nikodinovic-Runic I Guzik M Kenny ST Babu R Werker A
 472 assestos-containing rooming state and the reasonity of using recycled 473 waste sulfuric acid. J. Hazard. Mater. 265, 151–157. 	473	waste sulfulle acid. J. Hazard. Mater. 203, 131–137.
472 asbestos-containing rooming state and the reasonity of using recycled 473 waste sulfuric acid J Hazard Mater 265 151–157	473	Waste summer actual a mazatua Mater 200 $\pm 01-107$
472 asbestos-containing rooming state and the reasonity of using recycled		\mathbf{W}
472 asbestos-containing rooming state and the reastority of using recycled		waste sulfurie acid I Hezerd Mater 265 151 157
4/2 asbestos-containing rooming state and the reastority of using recycled		month guilturin and I Hazard Matar 765 151 157
472 aspestos-containing rooming state and the reastority of using recycled		waste sulfurio agid I Hazard Mater 265 151 157
472 aspestos-containing rooming state and the reastority of using recycled		waste sulfuria agid I Hazard Mater 265 151 157
4/2 aspestos-containing rooming state and the reasibility of using recycled		waste gulfurie egid. I. Hezerd. Meter. 265, 151, 157
470 achieved containing reating clote and the teachility of using reavaled	472	asbestos-containing roofing slate and the feasibility of using recycled
470 asherton containing reafing slate and the feasibility of using reavaled	472	asbestos-containing roofing slate and the feasibility of using recycled
470 ashestes containing reafing slate and the feasibility of using reavaled	472	asbestos-containing roofing slate and the feasibility of using recycled
470 ashestos containing reafing slate and the feasibility of using reavaled	472	asbestos-containing roofing slate and the feasibility of using recycled
	471	Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of
470 asherton containing reafing slate and the freshility of using rearrand	17 1	exhauted containing reafing date and the feasibility of using necessial
470 asherton containing reafing slate and the feasibility of using reavaled	472	ashestos-containing roofing slate and the feasibility of using recycled
470 ashestes containing reafing slate and the feasibility of using reavaled	472	asbestos-containing roofing slate and the feasibility of using recycled
470 ashestes containing reafing slate and the feasibility of using reavaled	472	asbestos-containing roofing slate and the feasibility of using recycled
470 asherton containing reafing slate and the feasibility of using reavaled	472	asbestos-containing roofing slate and the feasibility of using recycled
470 asherton containing reafing slate and the feasibility of using reavaled	472	asbestos-containing roofing slate and the feasibility of using recycled
470 ashestes containing reafing slate and the feasibility of using reavaled	472	asbestos-containing roofing slate and the feasibility of using recycled
	471	Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of
4/1 main, 510.5 joong, 5.5 Linn, 11.5 2014. Intermotinear destruction of	470 471	Nam S-N Jeong S Lim H 2014 Thermochemical destruction of
471 Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of	470	acids. Appl. Clay Sci. 52, 277–284.
 acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	469	cultivated on biodiesel-derived waste composed of glycerol and fatty
 acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	469	cultivated on biodiesel-derived waste composed of glycerol and fatty
 acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	469	cultivated on biodiesel-derived waste composed of glycerol and fatty
 acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	469	cultivated on biodiesel-derived waste composed of glycerol and fatty
 469 cultivated on biodiesel-derived waste composed of glycerol and fatty 470 acids. Appl. Clay Sci. 52, 277–284. 471 Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	468	bleaching in an oxane acid enficied medium by Asperginus inger
 469 cultivated on biodiesel-derived waste composed of glycerol and fatty 470 acids. Appl. Clay Sci. 52, 277–284. 471 Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	468	bleaching in an oxalic acid enriched medium by Aspergillus niger
 bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	407	Wushan, I., Clois, L., Kynnowicz, W., 2011. Designing a process of kaonin
 bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	467	Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin
 Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	466	acids recovery. Appl. Energy 147, 67-73.
 acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	465	deconstruction: an innovative strategy for biofuels and volatile fatty
 deconstruction: an innovative strategy for biofiders and volatile faity acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	A / F	deconstruction: on innovative strategy for hisfuels and velocile fatty
 deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	464	dry dark fermentation and mechanical pretreatment for lignocellulosic
 dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	463	Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of
 Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	462	toxicity reduction and bioremediation. J. Hazard. Mater. 341, 290–296.
 Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	460	toxicity reduction and bioromodiation I Hazard Mater 341 200 206
 toxicity reduction and bioremediation. J. Hazard. Mater. 341, 290–296. Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	461	mediated iron removal from chrysotile: Implications for asbestos
 mediated iron removal from chrysotile: Implications for asbestos toxicity reduction and bioremediation. J. Hazard. Mater. 341, 290–296. Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 	460	Christofidou-Solomidou, M., Willenbring, J.K., 2018. Siderophore-
 Christofidou-Solomidou, M., Willenbring, J.K., 2018. Siderophore- mediated iron removal from chrysotile: Implications for asbestos toxicity reduction and bioremediation. J. Hazard. Mater. 341, 290–296. Motte, JC., Sambusiti, C., Dumas, C., Barakat, A., 2015. Combination of dry dark fermentation and mechanical pretreatment for lignocellulosic deconstruction: an innovative strategy for biofuels and volatile fatty acids recovery. Appl. Energy 147, 67–73. Musiał, I., Cibis, E., Rymowicz, W., 2011. Designing a process of kaolin bleaching in an oxalic acid enriched medium by Aspergillus niger cultivated on biodiesel-derived waste composed of glycerol and fatty acids. Appl. Clay Sci. 52, 277–284. Nam, SN., Jeong, S., Lim, H., 2014. Thermochemical destruction of 		Monanty, S.K., Gonneau, C., Salamatipour, A., Pietrofesa, K.A., Casper, B.,

480	Plescia, P., Gizzi, D., Benedetti, S., Camilucci, L., Fanizza, C., De Simone,
481	P., Paglietti, F., 2003. Mechanochemical treatment to recycling
482	asbestos-containing waste. Waste Manag. 23, 209–218.
483	Rossi, S.C., Vandenberghe, L.P.S., Pereira, B.M.P., Gago, F. D., Rizzolo,
484	J.A., Pandey, A., Soccol, C.R., Medeiros, A.B.P. (2009). Improving
485	fruity aroma production by fungi in SSF using citric pulp. Food Research
486	International, 42(4), 484–486.
487	Saleem, M., Lavagnolo, M.C., Spagni, A., 2018. Biological hydrogen
488	production via dark fermentation by using a side-stream dynamic
489	membrane bioreactor: Effect of substrate concentration. Chem. Eng. J.
490	349, 719–727.

- 491 Sand, W., 1997. Microbial mechanisms of deterioration of inorganic
 492 substrates—a general mechanistic overview. International
 493 Biodeterioration & Biodegradation 40(2-4), 183–190.
- Sen, K.Y., Hussin, M.H., Baidurah, S., 2019. Biosynthesis of poly (3hydroxybutyrate)(PHB) by Cupriavidus necator from various pretreated
 molasses as carbon source. Biocatalysis and Agricultural
 Biotechnology, 17, 51–59.
- Shin, H.-S., Youn, J.-H., Kim, S.-H., 2004. Hydrogen production from food
 waste in anaerobic mesophilic and thermophilic acidogenesis. Int. J.
 Hydrogen Energy 29, 1355–1363.

501	Spasiano, D., 2018. Dark fermentation process as pretreatment for a
502	sustainable denaturation of asbestos containing wastes. J. Hazard.
503	Mater. 349, 45–50.
504	Spasiano, D., Luongo, V., Petrella, A., Alfè, M., Pirozzi, F., Fratino, U.,
505	Piccinni, A.F., 2017. Preliminary study on the adoption of dark
506	fermentation as pretreatment for a sustainable hydrothermal
507	denaturation of cement-asbestos composites. J. Clean. Prod. 166, 172-
508	180.
509	Spasiano, D., Luongo, V., Race, M., Petrella, A., Fiore, S., Apollonio, C.,
510	Pirozzi, F., Fratino, U., Piccinni, A.F., 2019. Sustainable bio-
511	hydrothermal sequencing treatment for asbestos-cement wastes. J.
512	Hazard. Mater. 364, 256-263.
513	Spasiano, D., Pirozzi, F., 2017. Treatments of asbestos containing wastes. J.
514	Environ. Manage. 204, 82–91.
515	Stayner, L., Welch, L.S., Lemen, R., 2013. The worldwide pandemic of
516	asbestos-related diseases. Annu. Rev. Public Health 34, 205–216.
517	Taghizadeh-Alisaraei, A., Hosseini, S.H., Ghobadian, B., Motevali, A.,
518	2017. Biofuel production from citrus wastes: A feasibility study in Iran.
519	Renewable and Sustainable Energy Reviews, 69, 1100–1112.

520	Wang, D., Cullimore, R., Hu, Y., Chowdhury, R., 2011. Biodeterioration of
521	asbestos cement (AC) pipe in drinking water distribution systems.
522	International Biodeterioration & Biodegradation 65(6), 810-817.
523	Wang, D., Zhang, D., Xu, Q., Liu, Y., Wang, Q., Ni, BJ., Yang, Q., Li, X.,
524	Yang, F., 2019. Calcium peroxide promotes hydrogen production from
525	dark fermentation of waste activated sludge. Chem. Eng. J. 355, 22–32.
526	Wong, N.P., LaCroix, D.E., McDonough, F.E., 1978. Minerals in whey and
527	whey fractions. J. Dairy Sci. 61, 1700–1703.
528	Zema, D.A., Fòlino, A., Zappia, G., Calabrò, P.S., Tamburino, V., Zimbone,
529	S.M., 2018. Anaerobic digestion of orange peel in a semi-continuous
530	pilot plant: An environmentally sound way of citrus waste management
531	in agro-ecosystems. Science of The Total Environment, 630, 401–408.
532	



Figure 1. Bio-H₂ production during the DF process by using orange pulp (\blacklozenge) and cheese whey (\blacklozenge) as biodegradable substrates. V_{sol} = 1.0 L. [ACW]_{100h} = 5 g L⁻¹. T = 35 °C.



Figure 2. Monitoring of OA production and the pH trend during the DF treatment carried out in the presence of cheese whey (a) and orange pulp (b). $V_{sol} = 1.0 \text{ L}$. [ACW]_{100h} = 5 g L⁻¹. T = 35 °C.



Figure 3. Net normalized magnesium and calcium concentration at the end of the DF process. $V_{sol} = 1.0 \text{ L. } [ACW]_{100h} = 5 \text{ g L}^{-1}$. T = 35 °C.



Figure 4. Effect of lactic acid (empty symbols) and oxalic acid (full symbols) loads on the HT treatment of the effluents deriving from the DF of cheese whey (a) and orange peel (b).

	Cheese whey	Orange	Glucose ^a
		peel	
[Butyric acid] (mM)	55.5	41.1	188.3
[Acetic acid] (mM)	45.6	62.7	38.5
[Lactic acid] (mM)	215.7	146.8	119.8
[Mg] _n /[Mg] _t before the HT treatment	0.41	0.36	0.48
[Mg] _n /[Mg] _t after 12 h HT treatment	0.90	0.86	0.93
(T=100 °C; 1.25 g L ⁻¹ lactic acid addition)	0.90	0.00	0.75

Table 1. Effect of the biodegradable substrate on the production and speciation of OAs and on the brucite-like layer dissolution. ^a Data reported in a previous study (Spasiano et al., 2019).

Conflict of Interest and Authorship Conformation Form

Please check the following as appropriate:

All authors have participated in (a) conception and design, or analysis and interpretation of the data; (b) drafting the article or revising it critically for important intellectual content; and (c) approval of the final version.



This manuscript has not been submitted to, nor is under review at, another journal or other publishing venue.

The authors have no affiliation with any organization with a direct or indirect financial interest in the subject matter discussed in the manuscript

• The following authors have affiliations with organizations with direct or indirect financial interest in the subject matter discussed in the manuscript:

Corresponding Author's name Danilo Spasiano Affiliation Polytechnic of Bari

Signature Solow

Supplementary materials

a) Analytical methods

The dissolved magnesium and calcium ion concentrations were measured by flame (acetylene/air) atomic absorption spectrometry (FAAS). For this purpose, a Varian Model 55B SpectrAA having a deuterium lamp for background correction was used.

Bio- H_2 concentration in the produced biogas was evaluated by gas chromatography (GC). For this purpose, a Varian Star 3400 equipped with a ShinCarbon ST 80/100 column and a thermal conductivity detector was used, adopting pure Ar as the carrier gas.

The concentrations of OAs were evaluated using a high-pressure liquid chromatography (HPLC) technique. The adopted equipment consisted of a Dionex AD25 absorbance detector, a Dionex GP 50bgradient pump and a Dionex LC 25 chromatography oven where a Metrohm Metrosep Organic Acids -250/7.8 column was housed. The eluent adopted during the analysis was a solution containing 0.5 mM sulfuric acid, and it was pumped at a flow rate of 0.7 mL/min.

The solids collected after the DF and HT processes were analysed with a FESEM-EDX Carl Zeiss Sigma 300 VP electronic microscope after a golden sputtering carried out with a Sputter Quorum Q150 under Ar atmosphere. In particular, the analysed solids were obtained from \approx 25 mL of suspension, which was dehydrated by means of a Martin Christ Alpha 1-4 LSCplus lyophilizer.

The TS, VS, and COD values were measured according to APHA standard methods (APHA, 1998). A pH-meter (HI 98190 pH/ORP; Hanna Instruments) was used to monitor the pH of the solutions.

b) Supplementary table

	[TS]	[VS]	[COD]	[Ca]	[Mg]
Orange pulp ^a	190	183	173.5	810×10 ⁻³	258×10-3
Cheese whey ^b	62	59	77.5×10^{3}	1061	248

Table 1S. Orange pulp and cheese whey characterization. ^a Results are reported in g kg⁻¹ of fresh weight. ^b Results are reported in mg L⁻¹.

c) Supplementary Figures



Figure 1S. SEM images of the suspension withdrawal after the DF step was carried out with cheese whey (a-b) and orange pulp (c-d). The highlighted parts represent the areas where the EDX analyses were performed.



Figure 2S. SEM images of the suspension withdrawal after the HT treatment (1.25 g/L lactic acid) of the effluents of the DF, carried out with orange pulp (a) and cheese whey (b). The highlighted sites represent areas where EDX analyses were performed.